

Steel Grade		Chemical Composition %				Mechanical Properties		
						Upper Yield Strength	Tensile Strength	Elongation
Steel Name	Steel Number	C max	Mn max	P max	S max	R _{eH} min (MPa)	R _m (MPa)	A min %
S195T	1.0026	0.20	1.40	0.035	0.030	195	320 to 520	20